


**PROCESS DETAILS**

Process	EPITAXIAL BASE
Die Size	66 X 66 MILS
Die Thickness	12.5 ± 1.0 MILS
Base Bonding Pad Area	12 X 24 MILS
Emitter Bonding Pad Area	11 X 14 MILS
Top Side Metalization	Al - 50,000Å
Back Side Metalization	Cr/Ni/Ag - 16,000Å

**GEOMETRY**



**GROSS DIE PER 4 INCH WAFER**







2,630

**PRINCIPAL DEVICE TYPES**

CJD31C  
MJE182  
TIP31C

145 Adams Avenue  
Hauppauge, NY 11788 USA  
Tel: (631) 435-1110  
Fax: (631) 435-1824  
www.centrasemi.com

R2 (1-August 2002)



145 Adams Avenue  
Hauppauge, NY 11788 USA  
Tel: (631) 435-1110  
Fax: (631) 435-1824  
www.centralsemi.com

R2 (1-August 2002)